

**Tabela kvaliteta nerđajućih čelika**

W.Nr.	DIN/ EN 10088-2	AISI	UNS	SS	JUS (SRPS)
1.4000	X6 Cr 13	403/410	S 41008	2301	Č4170
1.4005	X12 CrS 13	416	S 41600	2380	
1.4006	X12 Cr 13	410	S 41000	2302	Č4170
1.4016	X6 Cr 17	430	S 43000	2320	Č4174
1.4021	X20 Cr 13	420	S 42000	2303	Č4172
1.4024	X15 Cr 13	(410)	(S 41000)		Č4171
1.4028	X30 Cr 13	420 F	S 42020	2304	Č4173
1.4034	X46 Cr 13	(420)	(S 42000)	(2304)	Č4175
1.4057	X17 CrNi 16-2	431	S 43100	2321	Č4570
1.4104	X14 CrMoS 17	430 F	S 43020	2383	Č4790
1.4112	X90 CrMoV 18	440 B	S 44003		
1.4122	X39 CrMo 17-1				
1.4301	X5 CrNi 18-10	304	S 30400	2332	Č4580
1.4305	X8 CrNiS 18-9	303	S 30300	2346	Č4590
1.4306	X2 CrNi 19-11	304 L	S 30403	2352	Č45701
1.4307	X2 CrNi 18-9	304 L		2352	Č4580
1.4310	X10 CrNi 18-8	301	S 30100	2331	Č4571
1.4313	X3 CrNiMo 13-4	CA6-NM		2384	
1.4401	X5 CrNiMo 17-12-2	316	S 31600	2347	Č4573
1.4404	X2 CrNiMo 17-12-2	316 L	S 31603	2348	Č4574
1.4418	X4 CrNiMo 16-5-1			2387	
1.4432	X2 CrNiMo 17-12-3	316 L		2353	
1.4435	X2 CrNiMo 18-14-3	316 L	S 31603	2353	Č45704
1.4436	X3 CrNiMo 17-13-3	316	S 31600	2343	Č45706
1.4438	X2 CrNiMo 18-15-4	317 L	S 31703	2367	Č45705
1.4439	X2 CrNiMoN 17-13-5	(317 LMN)	S 31726		Č47702
1.4449	X5 CrNiMo 17-13	317	S 31700		
1.4460	X3 CrNiMoN 27-5-2	329	S 32900	2324	DUPLEX
1.4462	X2 CrNiMoN 22-5-3		S 31803	2377	DUPLEX
1.4529	X1 NiCrMoCuN 25-20-7		(S 31254)		
1.4539	X1 NiCrMoCu 25-20-5	(904 L)	N 08904	2562	
1.4541	X6 CrNiTi 18-10	321	S 32100	2337	Č4572
1.4542	X5 CrNiCuNb 16-4	630	S 17400		
1.4550	X6 CrNiNb 18-10	347	S 34700	2338	Č4582
1.4563	X1 NiCrMoCu 31-27-4		N 08028	2584	
1.4571	X6 CrNiMoTi 17-12-2	316Ti	S31635	2350	Č4574
1.4713	X10 CrAlSi 7				Č4974
1.4724	X10 CrAlSi 13				Č4972
1.4742	X10 CrAlSi 18				Č4973
1.4749	X18 CrN 28	446-1	S 44600	2322	
1.4762	X10 CrAlSi 25	(446)	(S 44600)	(2320)	Č4970
1.4821	X15 CrNiSi 25-4				
1.4828	X15 CrNiSi 20-12	309	(S 30900)		Č4577
1.4841	X15 CrNiSi 25-21	310/314	S 31400		Č4578
1.4845	X8 CrNi 25-21	310 S	S 31008	2361	
1.4864	X12 NiCrSi 35-16	330	N 08303		
1.4876	X10 NiCrAlTi 32-21	B 163			
1.4878	X8 CrNiTi 18-10	321	S 32100	2337	Č4572
1.4923	X22 CrMoV 12-1				

DIN = Deutsches Institut für Normung

AISI = American Iron and Steel Institute

UNS = Unified Numbering System

SS = Swedish Standard